



# UNITED STATES PATENT AND TRADEMARK OFFICE

UNITED STATES DEPARTMENT OF COMMERCE  
United States Patent and Trademark Office  
Address: COMMISSIONER FOR PATENTS  
P.O. Box 1450  
Alexandria, Virginia 22313-1450  
www.uspto.gov

APPLICATION NO.	FILING DATE	FIRST NAMED INVENTOR	ATTORNEY DOCKET NO.	CONFIRMATION NO.
09/857,540	07/23/2001	Sugio Miyazawa	939 026	6358

25191 7590 10/16/2003

BURR & BROWN

PO BOX 7068

SYRACUSE, NY 13261-7068

EXAMINER

DONG, DALEI

ART UNIT

PAPER NUMBER

2875

DATE MAILED: 10/16/2003

Please find below and/or attached an Office communication concerning this application or proceeding.

**Office Action Summary**

Applicati n No.

09/857,540

Applicant(s)

MIYAZAWA ET AL.

Examin r

Dalei Dong

Art Unit

2875

-- The MAILING DATE of this communication appears on the cover sheet with the correspondence address --  
Period for Reply

A SHORTENED STATUTORY PERIOD FOR REPLY IS SET TO EXPIRE 3 MONTH(S) FROM THE MAILING DATE OF THIS COMMUNICATION.

- Extensions of time may be available under the provisions of 37 CFR 1.136(a). In no event, however, may a reply be timely filed after SIX (6) MONTHS from the mailing date of this communication.
- If the period for reply specified above is less than thirty (30) days, a reply within the statutory minimum of thirty (30) days will be considered timely.
- If NO period for reply is specified above, the maximum statutory period will apply and will expire SIX (6) MONTHS from the mailing date of this communication.
- Failure to reply within the set or extended period for reply will, by statute, cause the application to become ABANDONED (35 U.S.C. § 133).
- Any reply received by the Office later than three months after the mailing date of this communication, even if timely filed, may reduce any earned patent term adjustment. See 37 CFR 1.704(b).

**Status**

- 1) ☒ Responsive to communication(s) filed on 11 September 2003.
- 2a) ☒ This action is **FINAL**. 2b) ☐ This action is non-final.
- 3) ☐ Since this application is in condition for allowance except for formal matters, prosecution as to the merits is closed in accordance with the practice under *Ex parte Quayle*, 1935 C.D. 11, 453 O.G. 213.

**Disposition of Claims**

- 4) ☒ Claim(s) 1-3 is/are pending in the application.
- 4a) Of the above claim(s) \_\_\_\_\_ is/are withdrawn from consideration.
- 5) ☐ Claim(s) \_\_\_\_\_ is/are allowed.
- 6) ☒ Claim(s) 1-3 is/are rejected.
- 7) ☐ Claim(s) \_\_\_\_\_ is/are objected to.
- 8) ☐ Claim(s) \_\_\_\_\_ are subject to restriction and/or election requirement.

**Application Papers**

- 9) ☐ The specification is objected to by the Examiner.
- 10) ☒ The drawing(s) filed on 11 September 2003 is/are: a) ☒ accepted or b) ☐ objected to by the Examiner.  
Applicant may not request that any objection to the drawing(s) be held in abeyance. See 37 CFR 1.85(a).
- 11) ☐ The proposed drawing correction filed on \_\_\_\_\_ is: a) ☐ approved b) ☐ disapproved by the Examiner.  
If approved, corrected drawings are required in reply to this Office action.
- 12) ☐ The oath or declaration is objected to by the Examiner.

**Priority under 35 U.S.C. §§ 119 and 120**

- 13) ☒ Acknowledgment is made of a claim for foreign priority under 35 U.S.C. § 119(a)-(d) or (f).  
a) ☒ All b) ☐ Some \* c) ☐ None of:
1. ☒ Certified copies of the priority documents have been received.
2. ☒ Certified copies of the priority documents have been received in Application No. 09/857,540.
3. ☐ Copies of the certified copies of the priority documents have been received in this National Stage application from the International Bureau (PCT Rule 17.2(a)).
- \* See the attached detailed Office action for a list of the certified copies not received.
- 14) ☐ Acknowledgment is made of a claim for domestic priority under 35 U.S.C. § 119(e) (to a provisional application).  
a) ☐ The translation of the foreign language provisional application has been received.
- 15) ☐ Acknowledgment is made of a claim for domestic priority under 35 U.S.C. §§ 120 and/or 121.

**Attachment(s)**

- 1) ☐ Notice of References Cited (PTO-892)
- 2) ☐ Notice of Draftsperson's Patent Drawing Review (PTO-948)
- 3) ☒ Information Disclosure Statement(s) (PTO-1449) Paper No(s) \_\_\_\_\_
- 4) ☐ Interview Summary (PTO-413) Paper No(s) \_\_\_\_\_
- 5) ☐ Notice of Informal Patent Application (PTO-152)
- 6) ☐ Other: \_\_\_\_\_

## DETAILED ACTION

### *Claim Rejections - 35 USC § 103*

1. The following is a quotation of 35 U.S.C. 103(a) which forms the basis for all obviousness rejections set forth in this Office action:

(a) A patent may not be obtained though the invention is not identically disclosed or described as set forth in section 102 of this title, if the differences between the subject matter sought to be patented and the prior art are such that the subject matter as a whole would have been obvious at the time the invention was made to a person having ordinary skill in the art to which said subject matter pertains. Patentability shall not be negated by the manner in which the invention was made.

2. Claims 1-3 are rejected under 35 U.S.C. 103(a) as being unpatentable over U.S. Patent 2No. 6,126,889 to Scott in view of U.S. Patent No. 5,683,949 to Scott.

Regarding to claims 1-3, Scott '889 discloses in Figure 1, "a ceramic metal halide (CMH) lamp assembly 10 according to the present invention. It is noted that both ends of the lamp assembly 10 are identical or substantially similar, therefore, only one end of the lamp assembly 10 is shown and described herein in detail. The lamp assembly 10 includes a high-pressure envelope or arc tube 12 which is transparent, end bushings or caps 14 sealing the open ends of the arc tube 12, and electrode assemblies 16 extending through and supported by the end caps 14 to form an arc within the sealed arc tube 12 when electrical current is applied to the electrode assemblies 16" (column 2, line 21-31).

Scott '889 also discloses in Figure 1, "the transparent arc tube 12 is formed from sapphire (single crystal alumina) which is fully dense. The arc tube can be produced in any suitable manner. See, for example, U.S. Pat. Nos. 5,427,051, 5,451,553, 5,487,353, 5,588,992, and 5,683,949, for suitable methods of producing sapphire arc tubes, the

disclosures of which are expressly incorporated herein in their entirety by reference” (column 2, line 32-38).

Scott ‘889 further discloses in Figure 1, “the end caps 14 are formed from a suitable polycrystalline ceramic material, preferably polycrystalline alumina, which is in an unsintered or "green state". The end caps 14 most preferably include about 0.02 to about 0.2 percent by weight MgO with polycrystalline alumina powder” (column 2, line 43-47).

Scott ‘889 further yet discloses in Figure 1, “each end cap 14 has a disc-shaped main wall 22, a cylindrically-shaped skirt or flange 24, and a tubularly-shaped extension 26 (capillary). The main wall 22 has a planar inner surface 28 facing the end surface of the arc tube 12 and a planar outer surface 30 facing away from the end surface of the arc tube 12” (column 2, line 55-61).

Scott ‘889 further yet discloses in Figure 1, “the flange 24 axially extends inward toward the arc tube 12 from the outer periphery of the main wall 22. The main wall 22 and flange 24 cooperate to form a cup or socket for receiving the end portion of the arc tube 12 therein. The flange 24 has a cylindrically-shaped inner surface 32 which has a diameter sized to form a sufficient monolithic seal with the outer surface 18 of the arc tube 12 as discussed in more detail hereinbelow. The length of the flange inner surface 32 is sized to provide a sufficient sealing area between the end cap 14 and the arc tube 12 as discussed in more detail hereinbelow” (column 2, line 62 to column 3, line 5).

Scott ‘889 further yet discloses in Figure 1, “the extension 26 axially extends outward from the outer surface 30 of the main wall 22 and is located generally at the

center of the main wall 22. The extension 26 and the main wall 22 cooperate to form an axially extending aperture or hole 34 which passes entirely through the end cap 14. The aperture 34 is sized and shaped to form a sufficient hermetic seal between the electrode assembly 16 and the end cap 14 as discussed in more detail hereinafter. Preferably, the aperture 34 is cylindrically-shaped. The length of the extension 26 is sized to provide sufficient support for the electrode assembly 16 and to provide a sufficient sealing area between the end cap 14 and the electrode assembly 16" (column 3, line 6-17).

However, Scott '899 does not disclose center body contain magnesium oxide 1.5 times less than capillary. Scott '949 teaches A starting material which has been found useful in the practice of this invention, wherein the polycrystalline body comprises polycrystalline alumina (PCA) and the PCA body is converted to single crystal alumina (hereinafter sapphire), is a bisque-fired body of relatively pure alpha alumina having an interconnected pore structure. An interconnected pore structure facilitates uniform penetration of the doping solution throughout the bisque-fired body. The typical starting bisque-fired material has a pore volume ranging from about 15-70%. In general, the starting material is a bisque-fired body composed of 99.9% alumina which can be sintered to densities greater than 3.90 g/cc after doping and is free of impurities of a type and amount that would prevent the conversion of the sintered PCA body to sapphire. When sintered, the bisque-fired body typically produces a PCA material having an equiaxed grain structure with average grain sizes less than 100 microns and preferably less than 70 microns. By grain size is meant the average dimension of a grain as measured by the well known linear intercept technique described in ASTM E112-88.

PCA materials with average grain sizes larger than 100 microns tend to form microcracks during the heat treatment of this invention which prevents the conversion to sapphire. The density of the sintered PCA should be at least 3.90 g/cc and more typically greater than 3.97 g/cc as the residual porosity can impede the conversion to sapphire and/or yield a sapphire product having less than optimal light transmittance” (column 4, line 58 to column 5, line 17).

Scott '949 also teaches in “in the production of sapphire in accordance with this invention, the starting bisque-fired material was bisque-fired alumina tubes used for the manufacture of Lucalox.RTM. tubes which have outer diameters ranging from 4.5 mm to 8.8 mm and wall thicknesses ranging from 0.5 mm to 0.75 mm. This bisque-fired material is available from General Electric Company, Willoughby Quartz and Ceramic Plant, Willoughby, Ohio (Product #LT5.5-36-PS; Resource #258 23 61). This bisque-fired material typically has a pore volume of 50-60%. When sintered, this material produces a PCA body having densities ranging from 3.97 g/cc to 3.98 g/cc and an equiaxed grain structure with average grain sizes ranging from 15-70 microns. A typical trace impurity analysis for the sintered material (undoped) is given in Table 1 below. The 180 wppm concentration of Magnesium (Mg) is equivalent to about 300 wppm magnesium oxide (MgO)” (column 5, line 18-33).

Scott '949 further teaches “magnesium oxide, typically added to alumina as a sintering aid to obtain a PCA body of densities greater than 3.97 g/cc, has been found to prevent the conversion of PCA to sapphire if present in sufficient quantity. Thus, steps must be taken to lower the magnesium oxide content of the fully dense doped PCA body

prior to conversion to sapphire. The level to which magnesium oxide must be lowered can depend on the type and amount of the dopant added. In some cases it has been found that it is necessary to reduce the magnesium content to as low as 50 wppm prior to converting the material to sapphire. Magnesium oxide content was determined using Inductively Coupled Plasma (ICP) analysis. Those skilled in the art know that magnesium oxide can be driven out of a PCA body by heating the body in a vacuum, dry hydrogen, or inert gas containing atmosphere to temperatures above 1600.degree. C. In the process of this invention, this was accomplished by heating the doped Lucalox.RTM. brand PCA in an electric resistance furnace to temperatures of 1880.degree. C. for approximately one to nine hours, depending on the part size, dopant type, and dopant level, in an atmosphere of dry hydrogen having a dew point below 0.degree. C. Times required to drive magnesium oxide from an alumina body will vary based on starting magnesium oxide content, furnace temperature, furnace atmosphere, and part dimension. Care must be taken during the magnesium oxide volatilization to avoid heating the material for too long as this can result in average grain sizes greater than 100. mu.m and/or anomalous grain growth" (column 5, line 43 to column 6, line 3).

Scott '949 further yet teaches "in accordance with this invention, the bisque-fired starting material is doped to a selected concentration with a conversion-enhancing dopant. As used herein, "conversion-enhancing dopant" refers to a dopant that, when introduced into the polycrystalline material at a concentration as described herein, reduces the time necessary to effect the solid state conversion of the polycrystalline material to a single crystal material during the heating process as discussed below. The

selected concentration of the dopant is less than the solid solubility level of the dopant in the polycrystalline material. The selected concentration of conversion-enhancing dopant thus is less than a concentration that will result in the formation of a second crystalline phase in the polycrystalline material. In doping the polycrystalline material, the dopant is typically dispersed in the polycrystalline material such that the concentration of the dopant is substantially homogeneous throughout the polycrystalline material. Based on dopant levels that have been investigated to date, it has been observed that conversion rate (from PCA to sapphire) generally increases as the concentration of the dopant is increased” (column 6, line 4-24).

It would have been obvious to one of ordinary skill in the art at the time the invention was made to have utilize the sapphire tube body doped with minimal amount of MgO of Scott ‘949 for the ceramic metal halide lamp assembly of Scott ‘889 in order to provide a transparent discharge arc tube and maintains the structural integrity of the tube and thus prolong the lifetime of the lamp assembly.

### ***Response to Arguments***

3. Applicant's arguments filed September 11, 2003 have been fully considered but they are not persuasive.

In response to Applicant primary argument that the prior art of record fails to teach or suggest an average grain diameter in a range of 10  $\mu\text{m}$  to 25  $\mu\text{m}$ ; Examiner asserts that Applicant does not establish the criticality of the range of values, no testing nor analysis that is not obvious to one having ordinary skill in the art had been conducted



to demonstrate the advantage and the criticality of the claimed ranges, further, it has been held that where the general conditions of a claim are disclosed in the prior, discovering the optimum or workable ranges involves only routine skill in the art. *In re Aller*, 105 USPQ 233. Thus, Examiner asserts that the prior art of record are valid and maintains the rejection.

### ***Conclusion***

4. **THIS ACTION IS MADE FINAL.** Applicant is reminded of the extension of time policy as set forth in 37 CFR 1.136(a).

A shortened statutory period for reply to this final action is set to expire THREE MONTHS from the mailing date of this action. In the event a first reply is filed within TWO MONTHS of the mailing date of this final action and the advisory action is not mailed until after the end of the THREE-MONTH shortened statutory period, then the shortened statutory period will expire on the date the advisory action is mailed, and any extension fee pursuant to 37 CFR 1.136(a) will be calculated from the mailing date of the advisory action. In no event, however, will the statutory period for reply expire later than SIX MONTHS from the mailing date of this final action.

Any inquiry concerning this communication or earlier communications from the examiner should be directed to Dalei Dong whose telephone number is (703)308-2870. The examiner can normally be reached on 8 A.M. to 5 P.M..


Application/Control Number: 09/857,540  
Art Unit: 2875

Page 9

If attempts to reach the examiner by telephone are unsuccessful, the examiner's supervisor, Sandra O'Shea can be reached on (703)305-4939. The fax phone number for the organization where this application or proceeding is assigned is (703) 872-9306.

Any inquiry of a general nature or relating to the status of this application or proceeding should be directed to the receptionist whose telephone number is (703)308-0956.

D.D.  
October 3, 2003

A handwritten signature in black ink, appearing to be "J. A. O'Shea", written over a faint, illegible stamp.